



AKRITAS

TECHNICAL DATA SHEET

MELAMINE FACED BOARD FOR INTERIOR USES

CHARACTERISTIC	TEST METHOD	UNIT	REQUIREMENT EN 14322	VALUE
Resistance to cracking (Αντίσταση στο ράγισμα)	EN 14323	Rating	≥ 3	≥ 4
Resistance to scratching (Αντίσταση στη χάραξη)	EN 14323	N	≥ 1,5	≥ 1,5
Resistance to staining (Αντίσταση στο λέκισμα με χημικά)	EN 14323	Rating	≥ 3	≥ 4
Resistance to surface wear (Αντίσταση στην εκδορά)	EN 14323	Class 1, 2, 3A, 3B, 4		3A
Resistance to cigarette burn [*] (Αντίσταση στο κάψιμο από τσιγάρο)	EN 14323 EN 438-2	Rating		> 3
Resistance to steam [*] (Αντίσταση στον ατμό)	EN 14323 EN 438-2	Rating		≥ 3
Surface soundness [*] (Αντίσταση στον επιφανειακό εφελκυσμό)	EN 311	Nt / mm ²	-	> 1,2
Formaldehyde release (Εκπομπή φορμαλδεΐδης)	ISO 12460-5	Class	-	E1
[*] Supplementary properties and test methods				

General Reference:

As a consequence of the constant improvement of our products, and/or possible changes of the relevant standards and legal requirements, no legal claim can be derived from the data in the product data sheet!

Quality Control Department
AKRITAS S.A.

AKRITAS A.E.
ΒΙΟΜΗΧΑΝΙΑ ΕΠΕΞΕΡΓΑΣΙΑΣ ΞΥΛΟΥ
Σωκ. Οικονόμου 3 Τηλ. 2551089810
ΕΔΡΑ ΑΛΕΞΑΝΔΡΟΥΠΟΛΗ
Α.Μ. 11141/06/Β/86/29 – ΑΦΜ 094058178